



TIVAR® 1000 ANTISTATIC

Anti-Static Ultra-High Molecular Weight PolyEthylene/Anti-Static UHMW PE



** TIVAR® is the registered trademark of

QUADRANT

PRODUCT CAPABILITIES:

- Rod : 3/8" - 2"
- Sheet : 1/4" - 2"

ADVANTAGES:

- Long-wearing
- High Impact Strength
- Light In Weight
- Self-lubricating
- Abrasion And Corrosion Resistant

PRODUCT COLORS:

- Black

APPLICATIONS INCLUDE:

- Dock Bumpers
- Protective Linings
- Conveyor Parts
- Bottling Wheels
- Bushings And Bearings
- Machined Parts
- Wear Strips
- Many Others

GENERAL PROPERTIES	ASTM or UL Test	TIVAR® 1000 ANTI-STATIC Typical Values
PHYSICAL		
Specific Gravity (g/cm ³)	D792	0.93
Water Absorption, 24 hrs (%)	D570	-
MECHANICAL		
Tensile Strength (psi)	D638	4000
Tensile Modulus (psi)	D638	-
Tensile Elongation at Break (%)	D638	140
Flexural Strength (psi)	D790	-
Flexural Modulus (psi)	D790	125,000
Compressive Strength (psi)	D695	2,000
Compressive Modulus (psi)	D695	-
Hardness, Shore D	D785	68
IZOD Notched Impact (ft-lb/in)	D256	No Break
THERMAL		
Coeff. of Thermal Expansion (x 10 ⁻⁵ in./in./°F)	D696	11 - 15
Heat Deflection Temp (°F / °C) @ 264 psi	D648	-
Glass Transition Temp (°F / °C)	D3418	-
Max Operating Temp (°F / °C)	-	180 / 82
Thermal Conductivity (BTU-in/ft ² -hr-°F)	C177	-
Flammability Rating	UL94	-
ELECTRICAL		
Surface Resistivity (ohms/sq)	D257	10 ⁵ - 10 ⁹
Volume Resistivity (ohm-cm) at 73°F, 50% RH	D257	10 ⁵ - 10 ⁹

NOTE: The information contained here in is typical values intended for reference only. They should NOT be used as a basis for design specifications or quality control.