



\*\* POMALUX® is the registered trademark of

## WESTLAKE PLASTICS COMPANY

### PRODUCT CAPABILITIES:

- Heavy Gauge Sheet :1/4" - 2"

### ADVANTAGES:

- Stainless Steel Filled
- Non-Sloughing
- Dimensionally Stable
- Extremely Strong And Stiff
- Highly Chemical Resistant
- Easily Machined

### PRODUCT COLORS:

- Black

### APPLICATIONS INCLUDE:

- Disk Drive Assembly Fixtures
- Handling Equipment In The Electrical/ Electronic Or Semiconductor Industry
- Telecommunication Hardware
- Automotive Equipment

GENERAL PROPERTIES	ASTM or UL Test	POMALUX® CN-SS Typical Values
<b>PHYSICAL</b>		
Specific Gravity (g/cm <sup>3</sup> )	D792	1.5
Water Absorption, 24 hrs (%)	D570	-
<b>MECHANICAL</b>		
Tensile Strength (psi)	D638	8,600
Tensile Elongation at Yield (%)	D638	-
Flexural Strength (psi)	D790	13,000
Flexural Modulus (psi)	D790	400,000
IZOD Notched Impact (ft-lb/in)	D256	0.7
IZOD Un-Notched Impact (ft-lb/in)	D256	-
Hardness, Shore D	D2240	86
<b>THERMAL</b>		
Coeff. of Thermal Expansion (x 10 <sup>-5</sup> in./in./°F)	D696	4.9
Heat Deflection Temp (°F / °C) @ 264 psi	D648	225 / 107
Thermal Conductivity (BTU-in/ft <sup>2</sup> -hr-°F)	C177	-
Flammability Rating @ .030"	UL-94	-
<b>ELECTRICAL</b>		
Surface Resistivity (ohms/sq)	D257	10 <sup>2</sup> - 10 <sup>6</sup>
Volume Resistivity (ohm-cm) at 73°F, 50% RH	D257	10 <sup>2</sup> - 10 <sup>6</sup>
Static Decay, 15% RH (seconds)	MIL-B-81705-B	-

NOTE: The information contained here in is typical values intended for reference only. They should NOT be used as a basis for design specifications or quality control.