

\*\* MACOR® is the registered trademark of

# CORNING

# **PRODUCT CAPABILITIES:**

· Rod : 1/4" - 2" · Sheet : 1/4" - 2"

### **ADVANTAGES:**

- · Continuous Use Temperature 800°C And Peak Temperature 1000°C
- · Coefficient Of Thermal Expansion Readily Matches Most Metals And Sealing Glasses
- · Exhibits Zero Porosity, And Unlike Ductile Materials, Won't Deform

# PRODUCT COLORS:

O White

# **APPLICATIONS INCLUDE:**

- · Ultra High Vacuum Environments
- · Constant Vacuum Applications
- · Microwave Spacers, Headers, Windows
- · Aerospace Industry Retaining Rings, Radiation Detectors
- · Welding Nozzles
- · Fixtures, Electrodes, Burner Blocks, Medical Equipment

GENERAL PROPERTIES	MACOR® MGC Typical Values
PHYSICAL	
Coefficient Of Expansion	
-100 – 25 °C	81 x 10 <sup>-7</sup> /°C
25 – 300 °C	90 x 10 <sup>-7</sup> /°C
25 – 600 °C	112 x 10 <sup>-7</sup> /°C
25 – 800 °C	123 x 10 <sup>-7</sup> /°C
Specific Heat @ 25°C	0.79kJ / kg°C
Thermal Conductivity @ 25°C	1.46 W/m°C
Thermal Diffusivity@ 25°C	7.3x10 <sup>-7</sup> m <sup>2</sup> /c
Continuous Operating Temperature	800°C
Maximum No Load Temperature	1000°C
MECHANICAL	
Density	2.52 g/cm <sup>3</sup>
Porosity	0%
Young's Modulus @ 25°C (Modulus Of Elasticity)	66.9 GPa
Poisson's Ratio	0.29
Shear Modulus @ 25°C	25.5 GPa
Hardness, Knoop 100g	250
Modulus Of Rupture @ 35°C (Flexural Strength)	94 MPa
Compressive Strength	345 MPa
ELECTRICAL	
Dielectric Constant @ 25°C, 1 KHz	6.01
Dielectric Constant @ 25°C, 8.5 GHz	5.64
Loss Tangent @ 25°C, 1 KHz	0.0040
Loss Tangent @ 25°C, 8.5 GHz	0.0025
Dielectric Strength, AC Or DC (0.3 mm Thickness @ 25°C)	45 KV/mm
DC Volume Resistivity @ 25°C	>10 <sup>17</sup> ohm-cm
CHEMICAL	(mg/cm²)
5% HCL (Hydrochloric Acid) @ 0.1 ph, 24hrs, 95°C	~ 100
0.002 N HNO <sub>3</sub> (Nitric Acid) @ 2.8 ph, 24hrs, 95°C	~ 0.6
0.1 N NaHCO <sub>3</sub> (Sodium Bicarbonate) @ 8.4 ph, 24hrs, 95°C	~ 0.3
0.02 N Na <sub>2</sub> CO <sub>3</sub> (Sodium Carbonate) @ 10.9 ph, 6hrs, 95°C	~0.1
5% NaOH (Sodium Hydroxide) @ 13.2 ph, 6hrs, 95°C	~10

NOTE: The information contained here in is typical values intended for reference only. They should NOT be used as a basis for design specifications or quality control.